

# HEY'DI PRODUCT DATA SHEET

FOR MORE PRODUCTS AND PRODUCT DOCUMENTATION SEE [WWW.HEYDI.NO](http://WWW.HEYDI.NO)



## HEY'DI K11 XTRA

Waterproof cement-based wash for plaster and concrete structures.

### Description

Hey'di K11 Xtra is a cement-based surfacing wash for all types of plaster and concrete structures. Hey'di K11 Xtra is mixed with water to produce a watertight surface.

### Areas of Use

Concrete foundations, lightweight clinker and concrete blocks, basements, tanks, wells, basins, dams, etc.; also usable as a negative side moisture barrier, or internal seal. Application temperature should be between +10 and +20 °C. Minimum temperature is +6 °C, which applies equally to the substrate.

### Preparation

The surface must be free from loose particles, dust, grease, etc. Pre-water it before each application, but avoid residual surface water.

### Mixing - Application

Hey'di K11 Xtra is mixed with clean water which is poured into the mixing tub first. Use approximately 3 litres of water to 10 kg powder. Small volumes may be stirred by hand, for larger volumes use a drill with a mixer attachment or a multi-purpose mixer. Leave the compound for 3-5 minutes before re-stirring and, if necessary, adding a little more water. The compound has an "open" time of about 45 minutes for application after mixing. By waiting these minutes before re-stirring the compound, you ensure that you

have the specified time available; alternatively, the compound may begin to set and the application "window" will be smaller.

Application is by grass brush. The next coat may be applied once the previous coat has set - normally after a few hours. The Hey'di K11 Xtra compound shall be easily brushed on but shall not run. Hey'di K11 Xtra will set like any other cement-based product; consequently, the ready mixed compound must be used continuously. Do not apply Hey'di K11 Xtra on warm plaster or in strong sunlight.

### Consumption

1 kg per sq.m per coat. A minimum of 2 coats must be applied; in the event of constant water pressure, 4 coats are recommended.

### Setting time

1-5 hours depending on temperature and substrate.

### Storage

Keep in a dry atmosphere for up to 2 years.

### Packaging

10 kilo bucket.



### TECHNICAL DATA

Water demand:.....approx. 3 l/10 kg  
Consumption:..... 1 kg/ per sq.m  
Max grain size: ..... 0,3 mm  
Pot life:..... 45 min.

### PRODUCT INFORMATION

#### Hey'di item number:

10 kilo:..... 1021

#### GTIN nr:

10 kilo:..... 7054150010214

#### Work Hygiene/Precautions

The product contains cement which, when mixed with water, may cause irritation to the skin and eye, nose and throat mucous membranes. Always read the warning on the packaging before starting work.

Revision date: 10.06.13